## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of Lorraine Leite, et al.		) Confirmation No.:	2254
Serial No.:	10/564,905	) Group Art Unit:	4181
Filing Date:	01/17/2006	) Docket No.: 99342	2.00061
GRA	ROXYAPALTITE CALCIUM PHOSPHATE NULES, METHOD FOR PREPARING SAME USES THEREOF	Customer No.:	21832

Mail Stop: Amendment Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450

## **RESPONSE TO OFFICE ACTION**

## Dear Sir/Madam:

In response to the Office Action mailed on February 3, 2008, applicant submits the following amendments to the specification and claims and remarks.

In the specification:

Please delete paragraph [0176] and replace it with the following:

[0176] Particle size is measured by laser light diffraction in aqueous suspensions without ultrasound and without dispersing agent, by means of a Beckman Coulter® LS230<sup>TM</sup> particle-size analyzer, by using Mie's theory.

Please delete paragraph [0198] and replace it with the following:

[0198] Granulates are prepared by loading the dry product thus obtained into a Fitzpatrick Chilsonator® roller/compactor system, equipped with 10-cm wide and 75-cm diameter rollers.

Please delete paragraph [0200] and replace it with the following:

[0200] The powdered mixture is fed by means of a moving belt into the Chilsonator® compacting device and is subjected to compacting by passage between the rollers.

Please delete paragraph [0203] and replace it with the following:

[0203] The product exists in the form of a sheet that is broken up by means of a Fitzmill®\*\*\*

(model DAS06) crushing device equipped with rotating cutting blades.

Please delete paragraph [0210] and replace it with the following:

[0210] The larger and smaller fractions that emerge from the vibrating sieves are sent to the Chilsonator®\*\*, mixed with the gross feed load for the Chilsonator®, and are then recycled.